g deposited with the U.S.

I hereby certify that this correspondence is being deposited with the U.S. Postal Service by First Class Mail in an envelope addressed to: Commissioner for Patents, Washington, DC 20231, on the date shown

Dated: June 25, 2002 Signature:

Cloen Shoffee

10/088840

Docket No.: NY-CHEMMT-206-US

8/19/02

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application of:

Klaus-Dieter NITTEL, et al.

Application No.: 10/088,840

Group Art Unit:

Filed: March 21, 2002

Examiner: Not Yet Assigned

For:

METHOD FOR APPLYING MANGANESE

PHOSPHATE LAYERS

PRELIMINARY AMENDMENT

Commissioner for Patents Washington, DC 20231 Box PCT

Dear Sir:

In advance of prosecution, please amend the above-identified patent application as follows:

IN THE CLAIMS

Please cancel claims 1-7, without prejudice and add the following new claims:

- 8. Method for applying manganese phosphate layers to iron or steel surfaces comprising contacting workpieces with a phosphating solution comprising
 - 0.2 to 4 g/l of iron (II) ions
 - 10 to 25 g/l of manganese ions
 - 25 to 50 g/l of phosphate ions (calc. As P_2O_5)
 - 3 to 35 g/l of nitrate ions
 - 0.5 to 5 g/l of nitroguanidine